


### Intended use

Fast-drying, highly weather-resistant and heavy-duty synthetic paint to coat commercial vehicles, machines and constructions. For interior and exterior use.

### Processing instructions

	<b>Mixing ratio</b>	<b>by weight (lacquer : hardener)</b>	<b>by volume (lacquer : hardener)</b>
	<b>hardener</b>	--	--



#### Hardener

--



#### Pot life

2 days with Mipa Härterverdünnung



#### Thinner

Mipa UN-Verdünnung  
Mipa Verdünnung UN 21  
Mipa Härterverdünnung



#### Spray viscosity gravity spray gun

20 - 25 s 4 mm DIN

#### Airmix/Airless

40 - 50 s 4 mm DIN



#### Application mode

<b>application mode</b>	<b>hardener</b>	<b>pressure (bar)</b>	<b>nozzle (mm)</b>	<b>spray passes</b>	<b>dilution</b>
gravity spray gun / HVLP	--	2,0 - 2,5	1,2 - 1,3	2 - 3	10 - 20 %
Airmix / Airless	--	100 - 120	0,23 - 0,28	1,5 - 2	5 - 10 %



#### Drying time

<b>hardener</b>	<b>object temperature</b>	<b>dust dry</b>	<b>set to touch</b>	<b>ready for assembly</b>	<b>sandable</b>	<b>recoatable</b>
--	20 °C	40 - 45 min	6 - 8 h	24 h	--	--
--	60 °C	--	--	1 h	--	--

Fully cured after 6 - 7 days (at 20 °C).

### Note

#### Characteristics:

binder base:	modified alkyd resin
solids content (% by weight):	50 - 56
solids content (% by volume):	39 - 41
delivery viscosity DIN 53211 4 mm (in s):	thixotropic
density DIN EN ISO 2811 (kg/l):	1,0 - 1,2
gloss level ISO 2813 at 60° (GU):	> 80 glossy

<b>Properties:</b>	short drying time highly resistant to UV and weathering high vertical stability excellent flow, high final hardness, retains the gloss over time resistant to petrol and diesel if exposed temporarily short-term heat exposure 150 °C permanent heat exposure 130 °C
<b>Theoretical spreading rate :</b>	33,2 - 40,5 m <sup>2</sup> /kg for 10 µm dry film thickness 39,5 - 41,4 m <sup>2</sup> /l for 10 µm dry film thickness
<b>Storage:</b>	at least 3 years in unopened original container
<b>VOC Regulation :</b>	This product contains the following maximum VOC-values: undiluted: < 520 g/l of VOC
<b>Processing conditions:</b>	from + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.
<b>Substrate preparation:</b>	Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!  Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate.  steel: - blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly - de-rust with hand and power tools to degree of cleanliness St 3 - degrease with Mipa WBS Reiniger or Mipa Silikonentferner
<b>Proposed coating structure:</b>	steel: priming coat: *AK 100-20 / AK 105-20 with 50 - 60 µm dry film thickness finishing coat: AK 240-90 with 50 - 60 µm dry film thickness  *Further Mipa primers are available. Please contact your technical adviser or our application technicians.
<b>Special notes:</b>	For professional use only.  Applying too thick layers may extend considerably the drying time.  Depending on the colour, the delivery viscosity may vary. Adjust the viscosity by adding thinner.  Check colour shade prior to application.
<b>Cleaning of tools:</b>	Clean tools immediately after use with Mipa Nitroverdünnung.